

Ambiance Sucupira

Preta FSC Engineered Board



LECA FLOR
CARPETS

30 YEARS OF PRODUCT AND SERVICE EXCELLENCE

Technical Specification Sheet

Board Width	70mm
Length	560mm
Thickness	10 mm
Construction	Top Layer Sawcut veneer of FSC Sucupira Preto, 4.2 mm; each top laminate is individually dried again to a wood moisture content of $8\% \pm 2\%$. No bevel
Finish	NATURA+ oiled (oxidatively dried)
End Use	Commercial
Quality	Select
Density	1000 / 1020 Kg/m ³ (Heavy wood)
Dimensional Stability	Excellent
Installation	Fully Adhered with approved wood flooring adhesive such as Sika T54 or T52 or F Ball B92 or B95
Important	A DPM is essential in new buildings, moisture content of both the air and subfloor should be taken prior to installation and retained. No claims will be entertained without this evidence. To maintain the parquet's quality and for human well-being, a healthy ambient temperature of 18 - 21°C is required, at a relative humidity of approx. 50 - 60%. If the humidity drops significantly during heating periods, we recommend the use of humidifiers to prevent the parquet floor from extreme drying. If the humidity is below normal, joints may be expected to widen. These normally close again after temperature has stabilised.
Country of Origin	Brazil – Certified Sustainable Forests
Areas Of Use	BMW Café/Customer Waiting Area
Specification	The floorcovering shall be Lecaflor Ambiance Sucupira Preto FSC Engineered Board fully adhered to the subfloor with special attention paid to acclimatization of the boards and relative humidity of both subfloor and air.

A finishing coat of Woca maintenance oil should be quickly wiped over the flooring post installation to ensure any scuffs or marks which may have been caused during installation are covered.



SOURCED FROM FSC APPROVED FORESTS



30 YEARS OF PRODUCT AND SERVICE EXCELLENCE